

CHEMIKO GUARD BLACK

Rubberised waterproof liquid membrane

1/1/2017



DESCRIPTION

CHEMIKO GUARD BLACK It is a scientific blend of synthetic resin, selected minerals and fillers. CHEMIKO GUARD BLACK is protective and waterproof coating with very high tensile strength. It is a high performance coating that dries to elastic, flexible, impermeable waterproof membrane.

BENEFITS/CHARACTERISTICS

- Single Component, Cold Applied and Highly Elastic Rubber like Membrane.
- Superior wetting & adhesion properties
- Unique Additives added to make it durable.
- Adapts itself over the irregular deck contours.
- Elongation properties more than >600%
- Requires no mixing or heating, saves labour cost and application time.
- Ensures durable bond & resists peeling, chipping, hence lasts longer.
- Highly Resistance to oxidation, UV & ozone.

CHEMICAL RESISTANCE, % WEIGHT CHANGE

- 10 % Salt (Sodium chloride) — 0
- 5 % Alkali (Caustic Soda) — 0
- 5 % Acid (Sulphuric) — 0
- Tack Free Time @ 35° C — 0-12 Hrs
- Drying Time @ 25° C — 30 - 40 Min.. (ASTM D 1640-03)
- Flammability & Toxicity — 0.95 ± 0.1
- Tensile Strength — 1.8 N / mm² (ASTM D 412-98)

USES

CHEMIKO GUARD BLACK is an Ideal waterproofing system for concrete roofs, polyurethane foam slabs, and polyester built up roofs, maintenance of existing roofs, masonry and concrete walls, Bridges ,Basement, Podium slabs, Green Areas, Planter boxes. Bathroom, decks, metal surfaces etc. It can be used as a sandwich membrane in new construction and as surface treatment on existing slabs,

TECHNICAL INFORMATION

Property	Value
Appearance	Smooth, Thick Paste
Color	Black
Specific Gravity	1.2 ± 0.10 (ASTM D 1644-03)
Solid Content %	60 ± 2 (ASTM D 1475-03)
Elongation @ Break	>600 % (ASTM D 2270-98)
Viscosity (Spindle No: 7; RPM: 10 @ 25°C)	50000 – 70000 CPS
Water Vapor Transmission (g/h-m ²)	0.46 (ASTM E 96-95)
Tensile Set Recovery, %	85

DISCLAIMER

The above information and details herein are based on the tests conducted & experience on application and usage. The user is advised to carry out the test and take trials to satisfy on the suitability of the products and meeting his requirement considering the prevailing conditions prior to apply/ using it on larger area. As the conditions under which the products are used or transported are beyond our control. We would not hold ourselves responsible on its consequential nonperformance.

CHEMIKO GUARD BLACK

Rubberised waterproof liquid membrane

1/1/2017



SURFACE PREPARATION

- The surface to be coated must be thoroughly cleaned and should be free of dirt, gravel, dust and oil. The concrete should be dry and smooth. When applying directly over concrete or old, dry asphalt, prime first with primer coat. When using as a top coat to protect and rejuvenate existing smooth asphalt roofs, first repair all blisters, cracks, split seams and flashing.

PRIMER

- For priming, primer coat of CHEMIKO GUARD BLACK is applied on prepared surface. For primer coat use CHEMIKO GUARD BLACK diluted with water in ratio of 1:2

FIRST AND SUCCEEDING COAT

- The coating is applied straight by using standard roofing brooms, brushes, squeegees or airless spray equipment, please check the viscosity to insure smooth spray of the product. Allow full curing of coating, (8 – 10 hours) before applying succeeding coats.
- For better results use Glass Fibre Reinforcement embedded into 1st Coat while it is still wet. To make the material more workable dilution with water upto 20% for 1st coat & upto 10% for 2nd coat is allowable.

COVERAGE

- Approximate coverage of CHEMIKO GUARD BLACK for a 2 coat application is around:
 - 40-50 sq. ft / kg in Metals
 - 30-50 sq. ft / kg in Asbestos
 - 30-40 sq. ft in Concrete
- depending on surface porosities. DFT of approx 300-400 microns will be achieved in 2 coats.

CLEANING

- Tools: Clean all the tools immediately with water. Use of thinner may be necessary for dried up material.
- Hands: Use a hand cleaner.

STORAGE & SHELF LIFE

- Shelf life is 12 months in unopened container. Store away from sunlight and preferably below 30oC. Storage should be frost protected.

DISCLAIMER

The above information and details herein are based on the tests conducted & experience on application and usage. The user is advised to carry out the test and take trials to satisfy on the suitability of the products and meeting his requirement considering the prevailing conditions prior to apply/ using it on larger area. As the conditions under which the products are used or transported are beyond our control. We would not hold ourselves responsible on its consequential nonperformance.

CHEMIKO GUARD BLACK

Rubberised waterproof liquid membrane

1/1/2017



HEALTH & SAFETY

As with all chemicals, caution should always be exercised. Protective clothing such as gloves and goggles should be worn.

- **INHALATION:** Inhalation of vapour or mist should be avoided. If inhaled symptoms include coughing, wheezing, laryngitis, and shortness of breath, headache, nausea, and vomiting. Immediately shift victim to fresh air, and, if needed immediately start artificial respiration. Give oxygen if breathing is laboured. Get emergency medical help.
- **EYE CONTACT:** Flush eyes with water for 15 minutes and call for medical help.
- **INGESTION:** Causes nausea, vomiting, and loss of consciousness. If accidentally swallowed do not induce vomiting rather call for medical help immediately.
- **SKIN CONTACT:** Flush with water or soap and water until all traces have been removed. Seek medical attention if required.

Available Packing : 1kg, 5kg, 10kg, 20kg, 25kg, 50kg, and 200kg

DISCLAIMER

The above information and details herein are based on the tests conducted & experience on application and usage. The user is advised to carry out the test and take trials to satisfy on the suitability of the products and meeting his requirement considering the prevailing conditions prior to apply/ using it on larger area. As the conditions under which the products are used or transported are beyond our control. We would not hold ourselves responsible on its consequential nonperformance.